



# DINO GRIP DECKING STRIPS

## Data Sheet

### DESCRIPTION

Dino Grip decking strips are high performance safety decking profiles, made from high quality FRP (Fibre Reinforced Plastic)/ GRP (Glass-fibre Reinforced Plastic). They are ideal for use in high traffic walkways, decking areas, pontoons, ramps, access bridges etc.

Wooden decking areas are notorious for becoming slippery when wet or with algae growth and the decking strips are an easy alternative for those slippery areas and can be installed for your own DIY Projects. The decking strips are also suitable for installation in any high trafficked areas where a quick anti-slip solution is required.

Our decking strips are quick and easy to install and are available in a range of colors and sizes and are suitable for DIY installations if required.

### CHARACTERISTICS

- Slip Resistant Surface
- Class 1 Flame Spread - Non Sparking
- Corrosion Resistant
- Lightweight
- Tough & Durable
- Choice of Colors
- Choice of Sizes
- Quick Installation
- Non Metallic

### APPLICATIONS

Ideal for use in high traffic walkways, decking areas, pontoons, ramps, access bridges etc.

Description	Slip Resistant Decking Profiles
Top Finish	Carbon and Silicon Grip Top Surface
Stock Colors	Brown, Black, Buff, Yellow, Grey and Hazard (Black/Yellow)
Thickness	Nominally 0.16" Thick
Chemical Resistance	Different Chemical Resistance Available, Please call our Technical Department for Advice

### TECHNICAL DATA

Decking Strip Weight (per metre)	1ft x 2" = 0.27 lbs 1ft x 3.5" = 0.47 lbs
Service Temperatures	-4°F to + 176°F
Fire Rating	The resin system used as standard is: Class 1
Design Life	10-15+ Years (subject to traffic analysis)
General Use	Standard Pedestrian Traffic

### SLIP RESISTANT LEVELS

Measured using the Pendulum test method (Four S rubber slider / 96 Slider) - standard simulated shoe sole.

Top Surface	Dry Reading	Wet Reading
Standard Grit Surface	80	75

The Slip Resistance Group guide to slip resistance of a floor for able bodied pedestrians.

Four S Pendulum Value	Potential For Slip
Above 65	Extremely Low
35 to 65	Low
25 to 65	Moderate
25 and Below	High

To ensure that the above slip resistant levels are maintained the decking strips should be kept clean in accordance with our cleaning guide and tips.